



Anti-Vegetativo Timiboat

Product Description

Anti-Vegetativo Timiboat is a recreational craft anti-fouling specifically developed to provide moderate anti-fouling and anti-vegetative protection for low fouling areas.

- * Protected whole season with moderate anti-fouling and anti-vegetative protection
- * Can be applied up to 3 months prior to release into water
- * Especially formulated to be used in fresh water and also in brackish water; it offers a good yield in salt water

Colour	Red Iron Oxid		
Gloss	Matt		
Specific Gravity	1,856 g/cm ³		
Solids by Weight (%)	76 %		
Mixing Ratio			
Thinning	Application	Brush or roller	Dil. p/ Anti-Veget. 1 Comp. N°3
		Spray	Dil. p/ Anti-Veget. 1 Comp. N°3
	Application	Brush or roller	9 to 11 m ² /Lt
		Spray	3 to 5 m ² /Lt
COV	500 g/Lt		
Available Packing	1 Lt and 5 Lt		

Drying / Repainting

	5°C	15°C	23°C	35°C
Touch Dry	1 hour	45 min	30 min	20 min
Repainting	Minimum: 8 hours / Maximum: Not determined			
Immersion	After 24 hours			

Application

Use and Specifications:	Previously painted Surfaces:
	<p>In good condition: Wash with a suitable detergent, wipe with fresh water and let dry. If the existing anti-vegetative coating is incompatible or if it is not known what the chemical nature is, seal with Primário Timicon 1 Comp. Cinzento.</p> <p>In poor condition: Remove all anti-vegetative paints in poor condition with the aid of paint stripper in this operation. If you need to sanding, never sanding at dry anti-vegetative paints or burning them to remove them. The anti-vegetative paints must only be sanded with at wet point with water.</p>



Anti-Vegetativo Timiboat

Application

Use and Specifications:

New Hulls:

All the preparation of the new surfaces (hulls) is detailed in the respective datasheets of the primers adapted to each situation.

Application:

Wooden Hulls

Grp Hulls

Steel/Iron Hulls

Lead Hulls

3 to 4 Coats

Application Method:

Brush, Roller or Conventional Spray

Utensils / Tools Cleaning:

The utensils/tools must be cleaned with **Dil. p/ Anti-Veget. 1 Comp. N°3** or **Diluyente Celuloso** immediately after the application.

Observations

Do not apply if there is the possibility of condensation forming on the substrate because it can cause gloss losses in the cure, which will take place at night.

The temperature of the product should be between 15 ° C and 35 ° C. The application temperature should be above 5 ° C and below 35 ° C. The temperature of the substrate should be above 5 ° C and below 30 ° C.

Avoid painting in direct sunlight.

Failure to apply the recommended number of coats will impact the durability and strength of the paint system (**Anti-Vegetativo Timiboat**).

The maximum immersion time must never exceed 6 months.

Do not apply Anti-Vegetativo Timiboat on boats with Aluminium hulls, corrosion reactions occur on the aluminium causing premature deterioration of the hull.

This technical data sheet is merely of an advisory nature, based on current technical know-how, for guidance, and may be changed without prior notice. As the conditions of application are beyond our control, the company cannot under any circumstances be held responsible for the obtained final results in its use.