



# TIMIGALVA – Gray Galvanized primer (4:1)

## DESCRIPTION

Primer formulated with modified alkyd resins, short in oil which may be hardened with isocyanates, anticorrosive pigments, specially formulated and developed for the painting of galvanized metal structures, both inside and outside and for anticorrosive protection structures in moderately aggressive environments. Characterized by easy application, fast drying, high filling power and good adherence. Adherent primer for galvanized sheet compatible with a wide range of finishing paints.

## SUPPLY FORM

2  
Endurecedor Timigalva (1)

## RECOMMENDED THINNER

**Diluyente S/R**

## THINNING

Conventional Spray – 10 to 15 %  
Airless spray – 5% max.

## PHYSICAL DATA

### COLOUR

Gray

### FILM ASPECT

Gloss

Matt

### SPECIFIC GRAVITY

1.560 ± 0.030 g/cm<sup>3</sup>

### VISCOSITY

85 - 95 KU

### SOLIDS BY WEIGHT

74 % - Theoretical value

### DRYING TIME

Touch dry  
Total dry

30 minutes  
2 - 4 hours

## APPLICATION DATA

### SURFACE PREPARATION

The surface must be free from all traces of grease, corrosion or any other contamination using a suitable solvent. Steel must be blast cleaned to Sa 2½ grade according to ISO 8501-1; if it is not possible it is recommended a power tool cleaning to St 3 grade according to ISO 8501-1.

### APPLICATION METHOD

Conventional spray, airless spray and brush

### RECOMMENDED FILM THICKNESS

Wet: 70 µm                      Dry: 38 µm

### THEORETICAL COVERAGE

8 to 12 m<sup>2</sup>/L/Per coat

### INTERVAL BETWEEN COATS (repainting)

At least 2 hours

### APPLICATION CYCLE (recommended finish)

Esmaltes Sintéticos (**Timisinte** or **Industrial S/R**),  
**PU** and **Epoxy**

### UTENSILS/TOOLS CLEANING

The utensils/tools must be cleaned with **Diluyente S/R** or **Diluyente Celuloso** immediately after the application.

This technical data sheet is merely of an advisory nature, based on current technical know-how, for guidance, and may be changed without prior notice. As the conditions of application are beyond our control, the company cannot under any circumstances be held responsible for the obtained final results in its use.



# TIMIGALVA – Gray Galvanized primer (4:1)

---

## ENVIRONMENTAL CONDITIONS DURING APPLICATION

Ambient Temperature	$\geq 5\text{ }^{\circ}\text{C}$
Relative Humidity	$\leq 80\%$
Surface Temperature	2 to 3 $^{\circ}\text{C}$ above dew point

## SHELF LIFE

When stored inside in original containers and sheltered from sunlight and cold at temperatures between 5 and 40  $^{\circ}\text{C}$ , the product has a shelf life of 3 years after its date of manufacture.

## OBSERVATIONS

- (1) -When used in polyurethane:
- Mixing ratio of components: volume – 4: 1 (**Timigalva primer / Endurecedor Timigalva**)
  - POT-LIFE of the Mixing: 1 to 2 hours.

## HEALTH, SAFETY AND ENVIRONMENT

In general, avoid contact with eyes and skin; gloves, goggles and appropriate clothing must be worn. Keep out of the reach of children. Use only in well ventilated areas. Do not empty into drains. Keep the container properly sealed and stored in the correct place. Take correct measures when transporting the product; Prevent any accident or incident that may occur during transportation, in particular the rupture or deterioration of the packaging. Ensure that the container is correctly stacked in a safe area. Do not store or use the product in extreme temperature conditions always between 5 and 40  $^{\circ}\text{C}$ . Always take account of the appropriate legislation relating to the Environment, Hygiene, Health and Safety at Work. For more information it is essential to read the label on the container and the product Material Safe Data Sheet.

## NOTE: RESERVED FOR PROFESSIONAL USERS

This technical data sheet is merely of an advisory nature, based on current technical know-how, for guidance, and may be changed without prior notice. As the conditions of application are beyond our control, the company cannot under any circumstances be held responsible for the obtained final results in its use.